

# Flexcon® OptiFlex® Conceal™ WPPM23313

Topcoated 2.3 Mil White Opaque, V-01 Adhesive, 1.2 Mil Poly Liner FLX057612

### **Benefits**

Adhesive complies with FDA 175.105 for indirect food contact

## **Features**

- 2.3 mil hard white opaque polypropylene (BOPP) metallized on one side for covering up pre-existing graphics
- Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks and hot stamping
- Excellent surface smoothness allows for optimum ink laydown
- High-performance, permanent acrylic adhesive adheres to a wide range of container types including low-surface energy HDPE
- Polyester release liner contains up to 60% Post Industrial Recycled content, provides good diecutting base and allows for high-speed dispensing

### **Additional Details**

### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Total Product	4.45	
Film	2.3 +/- 10 %	58
Adhesive	0.5-0.6 +/- 0.1	13-15 +/- 3
Liner	1.2 +/- 5%	30

Test Method: ASTM D 3652 (Modified for use with non-tape products)



# Flexcon® OptiFlex® Conceal™ WPPM23313

Topcoated 2.3 Mil White Opaque, V-01 Adhesive, 1.2 Mil Poly Liner FLX057612

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	54	594
Acrylic	52	572
Glass	40	440
Polypropylene	20	220
Styrene	42	462

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	5	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	730	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	35°F (1.7°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	ve

## **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.