



Flexcon® DrumCal™ 41521

3.1 Mil Topcoated White Vinyl, Permanent Adhesive, Layflat Liner - BS 5609 Compliant
FLX058668

Benefits

- The internal strength of the film facilitates removal during drum reconditioning
- BS 5609 compliant
- 2 year outdoor durability

Features

- 3.1 mil flexible white vinyl provides excellent chemical resistance for drum labeling applications
- Gloss topcoat yields excellent printability via laser, and UV, solvent and water flexo
- Adhesive system is designed to bond well to painted steel, fiber and plastic drums
- Product can be applied at low temperatures
- Permanent pressure-sensitive adhesive possesses good adhesion properties, tack and chemical resistance
- 74 lb. clay-coated release liner possesses excellent lay-flat properties
- Liner tracks well through laser printers and provides an excellent die-cutting base
- Designed for sheet-fed and roll-form laser printers

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	10.15	
Film	3.1 +/- 10%	79
Adhesive	0.9-1.0 +/- 0.1 (3)	23-25
Liner	6.0 +/- 10%	152

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Flexcon® DrumCal™ 41521

3.1 Mil Topcoated White Vinyl, Permanent Adhesive, Layflat Liner - BS 5609 Compliant
FLX058668

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	76	836
Acrylic	93	1023
Glass	74	814
Polypropylene	69	759
ABS	14	154

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	930	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	32°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.