



Flexcon® FlexMark® WP

3.5 Mil White Opaque Vinyl, Permanent Adhesive, Roll-to-Sheet Liner

FLX059984

Benefits

- Meets flammability requirements ASTM E 84 Class I or A Rated

Features

- 3.5 mil white opaque vinyl provides excellent hiding power
- Excellent printability via UV and solvent screen, UV and solvent inkjet, UV offset, and latex
- High-performance permanent adhesive bonds well to ABS, acrylic, Formica®, aluminum, stainless steel, HDPE, painted metal, styrene, painted non-vinyl wallboard, glass and more
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting

Additional Details

For Inkjet Printing: • Typical max. ink limit = 250% • When storing printed graphics, sheeted, stacked or in roll-form, consider leaving an unprinted margin (about 1/4") to allow for potential shrinkage of the film before trimming

Formica® is a registered trademark of the Diller Corp.

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	10.85	
Film	3.5 +/- 10 %	89
Adhesive	0.9-1.0 +/- 0.1	23-25 +/- 3
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape product)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	70	770
Aluminum	66	726
Glass	64	704
Polypropylene	24	264
Styrene	59	649

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	15	ASTM D 3654 Method Aa. 1 hr. dwellb. 1 sq. in. surfacec. 4 lb. load
Tack (g)	750	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information	Flammability: Contact Tech Service at 508-885-8263	
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.