Flexcon Flexcon® FlexMark® WPT

Topcoated 3.5 Mil White vinyl, Permanent Adhesive, Roll-to Sheet Liner FLX059988

Benefits

Features

- 3.5 mil white opaque vinyl provides excellent hiding power
- Primed for excellent ink adhesion and printability via UV and conventional offset, solvent and UV screen, solvent and water flexo, and solvent and UV inkjet
- High-performance permanent adhesive bonds well to ABS, acrylic, Formica®, aluminum, stainless steel, HDPE, painted metal, styrene, painted non-vinyl wallboard, glass and more
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting

Additional Details

For Inkjet Printing:• Typical max. ink limit = 250%; • When storing printed graphics, sheeted, stacked or in roll-form, consider leaving an unprinted margin (about 1/4") to allow for potential shrinkage of the film before trimming Formica® is a registered trademark of the Diller Corp.

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	11.55	
Film	3.5 +/- 10%	89
Adhesive	0.9-1.0 +/- 0.1 (3)	23-25
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape products)

Flexcon Flexcon® FlexMark® WPT

Topcoated 3.5 Mil White vinyl, Permanent Adhesive, Roll-to Sheet Liner FLX059988

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	70	770
ABS	62	682
Glass	64	704
Aluminum	66	726
Polypropylene	24	264

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	750	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.