



Benefits

- 1.5 mil super clear polyester release liner aids in ultra-smooth adhesive clarity
- Ideal for FDA 21CFR 211.132 and EU Falsified Medicines Directive (FMD) regulations for tamper-proof labeling and packaging
- 6-month change notification

Features

- 2.0 mil clear polypropylene offers excellent resistance to shrinkage, high temperatures, moisture, humidity and product contents
- Film clarity is ideal for achieving the no-label-look on clear vials and syringes
- Topcoat optimizes printability via narrow-format UV inkjet, flexographic, UV screen, UV letterpress, UV offset, and hot stamping
- Aggressive permanent rubber based adhesive offers excellent adhesion to plastic containers, cardboard, and packaging materials
- 1.5 mil super clear polyester release liner aids in ultra-smooth adhesive clarity

Additional Details

“Fit-for-use” testing is recommended under actual application conditions.

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|-----------------|-------------|
| Total Product | 4.54 | |
| Film | 2.0 +/- 10% | 51 |
| Adhesive | 0.7-0.8 +/- 0.1 | 18-20 +/- 3 |
| Liner | 1.4 +/- 5% | 36 |

Test Method: ASTM D 3652 (Modified for use with non-tape products)

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel | 84 | 924 |
| Acrylic | 83 | 913 |
| Glass | 83 | 913 |
| Polypropylene | 69 | 759 |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|---|--|
| Expected Shear (hours) | 100 | ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load) |
| Tack (g) | 1470 | ASTM D 2979 |
| Expected Exterior Life | Indoor use only | |
| Additional Information | | |
| Service Temperature | -40°F to 212°F (-40°C to 100°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.