



## Benefits

- The internal strength of the film facilitates removal during drum reconditioning
- BS 5609 compliant
- 2 year outdoor durability

## Features

- 3.1 mil flexible white vinyl provides excellent chemical resistance for drum labeling applications
- Gloss topcoat yields excellent printability via laser, and UV, solvent and water flexo
- Adhesive system is designed to bond well to painted steel, fiber and plastic drums
- Product can be applied at low temperatures
- 74 lb. clay-coated release liner possesses excellent lay-flat properties
- Liner tracks well through laser printers and provides an excellent die-cutting base
- Designed for sheet-fed and roll-form laser printers

## Additional Details

### Technical Data

#### Physical Properties

| Thickness (Mils [microns]) | Mils                | Microns |
|----------------------------|---------------------|---------|
| Total Product              | 10.15               |         |
| Film                       | 3.1 +/- 10%         | 79      |
| Adhesive                   | 0.9-1.0 +/- 0.1 (3) | 23-25   |
| Liner                      | 6.0 +/- 10%         | 152     |

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Acrylic            | 81            | 891   |
| Stainless Steel    | 77            | 847   |
| ABS                | 68            | 748   |
| Polypropylene      | 22            | 242   |
| Aluminum           | 75            | 825   |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties           | Value                                      | Test Method |
|---------------------------------|--|-------------|
| Expected Shear                  |  |             |
| Tack                            | 610  | ASTM D 2979 |
| Expected Exterior Life          | Two years                                  |             |
| Additional Information          |  |             |
| Service Temperature             | -40°F to 176°F (-40°C to 80°C)             |             |
| Minimum Application Temperature | 10°F (-12°C)                               |             |
| Storage Stability               | Two years stored at 70°F (21°C) and 50% RH |             |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.