



Benefits

Ideal for sheetfed offset printing

Features

- 3.5 mil flexible bright white opaque vinyl offers bright contrast for excellent graphic reproduction
- Film provides good opacity for covering up existing markings on the wall
- Film provides good resistance to scuffing, tearing and abrasion
- Excellent printability via UV and solvent screen, UV and solvent inkjet, UV offset, and latex
- Acrylic adhesive offers high initial tack and high ultimate bond to a wide variety of rough textured surfaces, including low surface energy plastics and painted metal
- High-performance adhesive system is designed to adhere to smooth surfaces as well as rough-textured surfaces
- High-performance permanent acrylic adhesive bonds well to ABS, aluminum and stainless steel surfaces
- High-performance, aggressive, permanent pressure-sensitive adhesive bonds well to a variety of surfaces
- Adhesive bonds well to PVC, Varnished Wood, Lumber/Wood, Paint, and Ceramic
- Adhesive has high peel and high shear characteristics resistant to cold flow and ooze
- 94 lb. premium grade moisture stable polycoated layflat release liner provides excellent stay flat release liner properties for printing and converting

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	11.9	
Film	3.5 +/- 10%	89
Adhesive	1.9-2.1 +/- 0.1	48-53 +/- 3
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Flexcon® FLEXmark® BILBRD™ BWV RTS

Outdoor Signage: Walls Graphics for Rough-Textured Surfaces
FLX000619

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Rough Textured Concrete	3	33

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	15	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	750	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.