



## Benefits

## Features

- 1.0 mil white opaque permanent acrylic transfer adhesive
- Backed with two 50lb. semi-bleached white kraft release liners ideal for roll-to-roll converting

## Additional Details

## Technical Data

### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	7.45	
Adhesive	1.0-1.1 +/- 0.1	25-28 +/- 3
Liner	SPEC 50K-8 Liner: 3.1 +/- 10	79
Liner 2	SPEC 50K-9 Liner: 3.1 +/- 10	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)

**Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	55	605
Glass	60	660
Polypropylene	10	110
Acrylic	56	616

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	100 +	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	640	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

**Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.