



### Benefits

- Product has the ability to adhere to curved compound surfaces and rivets without lifting.

### Features

- 3.5 mil flexible soft clear vinyl film provides excellent conformability for compound curved surface
- Printable via UV and solvent flexo
- High-performance, permanent, pressure-sensitive acrylic adhesive bonds well to base film
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting

### Additional Details

### Technical Data

#### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	11.75	
Film	3.5 +/- 10 %	89
Adhesive	1.0-1.1 +/- 0.1	25-28 +/- 3
Liner	6.9 +/- 10 %	175

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	47	517
Acrylic	60	660
Glass	54	594
Polypropylene	14	154

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	15	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	500	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Six months stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.