



## Flexcon® OptiFlex® Reseal™ 20133

Topcoated 2.0 Mil Clear BOPP, High-Performance Resealable Adhesive, TracRite™ 120  
FLX064722

### Benefits

- Excellent surface smoothness allows for optimum ink laydown
- Adhesive complies with 21 CFR 175.105 for indirect food contact
- Order custom widths without purchasing a whole master through [Flexcon® FlexChoice™ for Packaging](#)

### Features

- 2.0 mil clear polypropylene (BOPP) offers excellent resistance to shrinkage, moisture, humidity and product contents
- Film offers excellent tear resistance and durability for opening and reclosure of flexible packaging substrates
- Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks, and hot stamping
- Resealable pressure-sensitive acrylic adhesive bonds well to low- and high- surface energy laminated flexible packaging substrates with clean, quiet and consistent reclosure
- Adhesive offers excellent clarity and wet out characteristics
- Polyester release liner for excellent on-press performance for tight-registration graphics & contains up to 60% post industrial recycled content

### Additional Details

#### Technical Data

##### Physical Properties

| Thickness (Mils [microns]) | Mils            | Microns     |
|----------------------------|-----------------|-------------|
| Total Product              | 4.2             |             |
| Film                       | 2.0 +/- 10 %    | 51          |
| Adhesive                   | 0.7-0.8 +/- 0.1 | 18-20 +/- 3 |
| Liner                      | 1.2 +/- 10 %    | 30          |

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel    | 19            | 209   |
| Acrylic            | 21            | 231   |
| Glass              | 16            | 176   |
| Polypropylene      | 8             | 88    |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties           | Value   | Test Method   |
|---------------------------------|---|---|
| Expected Shear (hours)          | Room Temp (hours): 100+                                   | ASTM D 3654 Method A<br>a. 1 hr. dwell<br>b. 1 sq. in. surface<br>c. 4 lb. load |
| Tack (g)                        | 440   | ASTM D 2979   |
| Expected Exterior Life          | Indoor use only   |   |
| Additional Information          |   |   |
| Service Temperature             | -20°F to 212°F (-29°C to 100°C)                           |   |
| Minimum Application Temperature | 50°F (10°C)   |   |
| Storage Stability               | Two years stored at 70°F (21°C) and 50% relative humidity |   |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.