



Flexcon® FlexMark® OL 500 Clear Velvet L-344 TracRite™ 100

Durable Goods and Equipment Labeling Clear Velvet Embossed Polycarbonate - Overlamine
FLX065368

Benefits

- UL recognized under UL 969 - UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component
- CSA accepted under CSA File No. 99214

Features

- 5.0 mil clear velvet embossed overlaminating polycarbonate adds texture and protection to printed graphics
- Durable polycarbonate offers exceptional resistance to scratches and fingerprints
- Permanent pressure-sensitive acrylic adhesive bonds well to base film substrates
- Flexcon® TracRite™ 100 polyester release liner provides excellent clarity and surface smoothness, and is an excellent diecutting base

Additional Details

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|-----------------|------------|
| Total Product | 7.3 | |
| Film | 5.0 +/- 10 % | 127 |
| Film 2 | 5.0 +/-10% | |
| Adhesive | 1.2-1.3 +/- 0.1 | 30-33 +/-3 |
| Liner | 1.0 +/- 10 % | 25 |

Test Method: ASTM D 3652 (Modified for use with non-tape product)

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel | 61 | 671 |
| Acrylic | 68 | 748 |
| Glass | 68 | 748 |
| Polypropylene | 48 | 528 |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|---|---|
| Expected Shear (hours) | 100 | ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load) |
| Tack (g) | 900 | ASTM D 2979 |
| Expected Exterior Life | Indoor use only | |
| Additional Information | | |
| Service Temperature | -40°F to 212°F (-40°C to 100°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.