



## Flexcon® JetBond® 44138BN

4.0 Mil Frosty Clear Overlaminating Vinyl, Permanent Adhesive, Kraft Release Liner  
FLX066520

### Benefits

- Luster finish reduces glare on printed graphics for better visibility
- Smooth natural (tan) Kraft release liner helps ensure smooth flow-out of adhesive on the overlaminating film
- Natural (tan) Kraft liner manufactured with less energy than bleached (white) liners. No bleach wastewater to be treated from the manufacturing process

### Features

- 3.5 mil luster overlaminating vinyl film increases dimensional stability
- Film is designed to protect printed graphics from abrasion and taxi-cleaning solvents
- UV absorbing/resistant high-performance permanent acrylic pressure-sensitive adhesive enhances and provides added protection to digitally-printed graphics
- Adhesive bonds well to printed base surface
- Backed with a 44 lb. polycoated natural Kraft release liner

### Additional Details

This product is part of Flexcon's Outdoor Wall Graphics Advertising System, use base film [Flexcon® FlexMark® BilBrd™ BWV](#).

### Technical Data

#### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	7.75	
Film	3.5 +/- 10%	89
Adhesive	1.0-1.1 +/- 0.1	25-28 +/- 3
Liner	3.1 +/- 10%	79

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	76	836
Glass	68	748
Stainless Steel	61	671

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	70	ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq. in. surface c. 4 lb. load
Tack (g)	430	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.