



### Benefits

- 5 year outdoor durability

### Features

- 5.0 mil clear velvet overlaminate polycarbonate that protects against damaging UV rays, moisture & scratching
- Permanent pressure-sensitive acrylic adhesive bonds well to printed film
- Backed with an ultra-smooth clear polyester release liner

### Additional Details

### Technical Data

#### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	7.84	
Film	5.0 +/- 10 %	127
Adhesive	1.4-1.5 +/- 0.1	36-38 +/- 3
Liner	1.4 +/- 10 %	36

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	61	671
Acrylic	68	748
Glass	68	748
Polypropylene	48	528

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	100	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	900	ASTM D 2979
Expected Exterior Life	5 Years based on 2000 hours Xenon arc weatherometer exposure	
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.