



Flexcon® PharmCal® Supreme 068639 (PharmCal® PP 260 H White TC-272 V-344 TracRite™ 150)

2.6 Mil White Polypropylene, Permanent Adhesive, Poly Liner
FLX068639

Benefits

- 21 CFR 175.105; ISO 10993-5, -10 compliant*
- 6-month change notification

Features

- 2.6 mil white polypropylene offers excellent resistance to shrinkage, high temperatures, moisture, humidity and product contents
- Topcoat optimizes printability with flexographic, rotary screen, rotary letterpress inks and hot stamping
- Permanent aggressive adhesive provides a high ultimate bond, and excellent tack, clarity, and wet out characteristics
- High-adhesive performance bonds to tight-radius glass or plastic containers
- Biocompatible adhesive mitigates risk of migration through packaging
- Flexcon® TracRite™ 150 polyester release liner for excellent on-press performance for tight registration graphics
- Release liner is ideal for roll-form applications that require high-speed dispensing

Additional Details

*FDA CFR 175.105: Adhesives may be safely used as components of articles intended for use in packaging, transporting, or holding food in accordance with the following prescribed conditions. ISO 10993 Biological evaluation of medical devices: Part 5:Tests for in vitro cytotoxicity; Part 10:Tests for irritation and skin sensitization.

"Fit-for-use" testing is recommended under actual application conditions.

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|-----------------|-------------|
| Total Product | 5.14 | |
| Film | 2.6 +/- 10 % | 66 |
| Adhesive | 0.7-0.8 +/- 0.1 | 18-20 +/- 3 |
| Liner | 1.4 +/- 5 % | 36 |

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Flexcon® PharmCal® Supreme 068639 (PharmCal® PP 260 H White TC-272 V-344 TracRite™ 150)

2.6 Mil White Polypropylene, Permanent Adhesive, Poly Liner
FLX068639

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Glass | 48 | 528 |
| Polypropylene | 19 | 209 |

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|---|---|
| Expected Shear (hours) | 40 | ASTM D 3654 Method Aa. 1 hr. dwellb. 1 sq. in. surfacec. 4 lb. load |
| Tack (g) | 750 | ASTM D 2979 |
| Expected Exterior Life | Indoor use only | |
| Additional Information | | |
| Service Temperature | -40°F to 212°F (-40°C to 100°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.