

## Flexcon® NexGen™ SMP344S

Gloss topcoated 2.0 mil silver matte polyester for durable labeling FLX068715

### **Benefits**

- 2.0 mil gloss topcoated silver matte polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Topcoat is more universally printable than other thermal transfer printable products
- Printable via resin and wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; and UV inkjet
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate
  and fiberglass
- High shear and high peel adhesive resists cold flow and oozing
- Adhesive bonds well to base film substrates
- 90 lb. moisture stable polycoated release liner is ideal for roll-to-sheet and sheet-form converting on most narrow-format presses

#### **Features**

### **Additional Details**

- UL recognized under UL 969 UL File No. PGJI2.MH16635 Printing Materials Component
- cUL recognized under UL File No. PGJI8.MH16635 Printing Materials Certified for Canada Component under CAN/CSA standard C22.2, No. 0.15

### **Technical Data**

#### **Physical Properties**

| Thickness (Mils [microns]) | Mils                | Microns |
|----------------------------|---------------------|---------|
| Total Product              | 9.85                |         |
| Film                       | 2.0 +/- 10%         | 51      |
| Adhesive                   | 0.9-1.0 +/- 0.1 (3) | 23-25   |
| Liner                      | 6.9 +/- 10%         | 175     |

Test Method: ASTM D 3652 (Modified for use with non-tape products)



# Flexcon® NexGen™ SMP344S

Gloss topcoated 2.0 mil silver matte polyester for durable labeling FLX068715

#### **Adhesion Properties**

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Acrylic            | 77            | 847   |
| Stainless Steel    | 55            | 605   |
| Glass              | 68            | 748   |
| Polypropylene      | 15            | 165   |
| ABS                | 60            | 660   |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties           | Value                                      | Test Method |
|---------------------------------|--|-------------|
| Expected Shear (hours)          |  |             |
| Tack (g)                        | 1030                                       | ASTM D 2979 |
| Expected Exterior Life          | Two years                                  |             |
| Additional Information          |  |             |
| Service Temperature             | -40°F to 302°F (-40°C to 150°C)            |             |
| Minimum Application Temperature | 50°F (10°C)                                |             |
| Storage Stability               | Two years stored at 70°F (21°C) and 50% RH |             |

## **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.