G Flexcon Flexcon® NexGen™ WV344H

4.0 Mil Gloss Topcoated White Vinyl, Permanent Adhesive, Roll Form Liner (1.9-2.1) FLX068720

Benefits

- UL recognized under UL 969 UL File No. PGGU2.MH10170 Printing Materials Component
- cUL recognized under UL File No. PGGU8.MH10170 Printing Materials Certified for Canada Component under CAN/CSA standard C22.2, No. 0.15

Features

- Gloss topcoated 4.0 mil white flexible vinyl provides consistent surface smoothness, excellent dimensional stability, and conformability
- Printable via resin and wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; laser (toner); and narrow-format UV inkjet
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate
 and fiberglass
- High shear and high peel adhesive resists cold flow and oozing
- Adhesive bonds well to base film substrates
- Backed with a 50 lb. bleached kraft release liner ideal for roll-form converting
- Liner is suitable for optical sensing on most thermal transfer printers

Additional Details

All narrow-format UV inkjet systems are different; therefore, we recommend "fit-for-use" testing.

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	8.9	
Film	3.5 +/- 10%	89
Adhesive	1.9-2.1 +/- 0.1 (3)	48-53
Liner	3.1 +/- 10%	79

Test Method: ASTM D 3652 (Modified for use with non-tape products)

G Flexcon Flexcon® NexGen[™] WV344H

4.0 Mil Gloss Topcoated White Vinyl, Permanent Adhesive, Roll Form Liner (1.9-2.1) FLX068720

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	148	1628
Stainless Steel	108	1188
ABS	84	924
Polypropylene	66	726
Aluminum	91	1001

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	880	ASTM D 2979
Expected Exterior Life	Five years based on 2000 hrs. Xenon Arc	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.