Flexcon® NexGen™ WV344S

4.0 Mil Print-Receptive White Vinyl, Permanent Adhesive, Sheet-Form Liner

FLX068721

Benefits

- UL recognized under UL 969 – UL File No. PGGU2.MH10170 Printing Materials – Component
- cUL recognized under UL File No. PGGU8.MH10170 – Printing Materials Certified for Canada – Component – under CAN/CSA standard C22.2, No. 0.15
- View Flexcon® NexGen™ WV344S Yellow Card

Features

- 3.5 mil flexible white vinyl provides good surface smoothness and conformability
- Print-receptive 4.0 mil white flexible vinyl provides consistent surface smoothness, excellent dimensional stability, and conformability
- Printable via thermal transfer, UV and solvent screen, UV, solvent & water flexo, and narrow-format UV inkjet
- In most cases, corona treatment is not required
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass
- High shear and high peel adhesive resists cold flow and oozing
- Adhesive bonds well to base film substrates
- 90 lb. moisture stable polycoated release liner is ideal for roll-to-sheet and sheet-form converting on most narrow-format presses

Additional Details

All narrow-format UV inkjet systems are different; therefore, we recommend "fit-for-use" testing.

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	10.95	
Film	3.5 +/- 10%	89
Adhesive	0.9-1.0 +/- 0.1 (3)	23-25
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape product)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	101	1111
Glass	64	704
Polypropylene	24	264
Aluminum	99	1089
Acrylic	69	759

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	750	ASTM D 2979
Expected Exterior Life	Five years based on 2000 hrs Xenon Arc	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.

© 2026 Flexcon, Inc. All rights reserved.