

Benefits

• Topcoat is more universally printable than other thermal transfer printable products

Features

- 2.0 mil white gloss topcoated polyester provides consistent surface smoothness, excellent dimensional stability and endurance to varying temperatures
- Printable via resin and wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; and UV inkjet
- High-adhesive bond onto plastic containers, cardboard, and packaging materials
- Backed with a 50 lb. semi-bleached kraft release liner that is Quilon® coated

Additional Details

*Quilon® is a registered trademark of Zaclon, LLC.

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	6.95	
Film	2.0 +/- 10 %	51
Adhesive	1.3-1.4 +/- 0.1	33-36 +/- 3
Liner	3.1 +/- 10 %	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	118	1298
Acrylic	132	1452
Glass	129	1419
Polypropylene	15	165

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method	
Expected Shear (hours)	10	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)	
Tack (g)	870	ASTM D 2979	
Expected Exterior Life	Two years		
Additional Information			
Service Temperature	-40°F to 302°F (-40°C to 150°C)	-40°F to 302°F (-40°C to 150°C)	
Minimum Application Temperature	32°F (0°C)		
Storage Stability	Two years stored at 70°F (21°C) and 50% relat humidity	tive	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.