



## Benefits

- Polypropylene is more economical and conformable than polyester and provides a good diecutting base
- Excellent surface smoothness allows for optimum ink laydown
- Adhesive separates cleanly from PET flake during the recycling process allowing for the collection of rPET
- Product has been 3rd party tested for Higher Pressure Processing (HPP) and adhesive was found to have the necessary strength and compatibility to withstand the HPP conditions
- APR Critical Guidance Recognition - Flexcon's undecorated OptiFlex® EcoFocus® PP 230 H White TC pressure-sensitive labels, with V-52RE adhesive meet or exceed APR's Critical Guidance Protocol for Clear PET Articles with Labels and Closures.
- Order custom widths without purchasing a whole master through Flexcon® FlexChoice™ for Packaging

## Features

- Topcoated 2.3 mil white polypropylene offers excellent resistance to shrinkage, moisture, humidity, and product contents
- Film conformability for rigid containers provides maximum label and graphic coverage
- Printable via UV, solvent & water flexo, narrow-format UV inkjet, roll-form dry toner, UV rotary screen, UV letterpress and hot stamping
- High-performance adhesive adheres well to PET containers
- Polyester release liner for excellent on-press performance for tight-registration graphics & contains up to 60% post industrial recycled content

## Additional Details

### Technical Data

#### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	4.45	
Film	2.3 +/- 10%	58
Adhesive	0.5-0.6 +/- 0.1	13-15 +/- 3
Liner	1.2 +/- 5%	30

Test Method: ASTM D 3652 (Modified for use with non-tape products)



**Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	30	330
Polyester	24	264

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	10	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in. surface, 4 lb. load)
Tack (g)	500	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	20°F (-6.6°C)	
Storage Stability	Two years when stored at 70°F (21°C) and 50% relative humidity	

**Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.