

Flexcon® NexGen™ WV778

4.0 Mil Gloss Topcoated White Vinyl, Permanent Adhesive, Roll-Form Liner FLX068961

Benefits

- UL recognized under UL 969 UL File No. PGGU2.MH10170 Printing Materials Component
- cUL recognized under UL File No. PGGU8.MH10170 Printing Materials Certified for Canada Component under CAN/CSA standard C22.2, No. 0.15

Features

- Gloss topcoated 4.0 mil white flexible vinyl provides consistent surface smoothness, excellent dimensional stability, and conformability
- Printable via resin and wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; laser (toner); and narrow-format UV inkjet
- High-performance modified acrylic pressure-sensitive adhesive is the most aggressive adhesive for low surface energy plastics
- · Permanently bonds to a variety of low surface energy plastics, painted metal, powder coated paint, polycarbonate, and fiberglass
- Adhesive eliminates the need to prime or flame treat the surface of TPO plastics
- Backed with a 50 lb. bleached kraft release liner ideal for roll-form converting
- Liner is suitable for optical sensing on most thermal transfer printers

Additional Details

All narrow-format UV inkjet systems are different; therefore, we recommend "fit-for-use" testing.

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|---------------------|---------|
| Total Product | 7.95 | |
| Film | 3.5 +/- 10% | 89 |
| Adhesive | 1.0-1.1 +/- 0.1 (3) | 25-28 |
| Liner | 3.1 +/- 10% | 79 |

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Flexcon® NexGen™ WV778

4.0 Mil Gloss Topcoated White Vinyl, Permanent Adhesive, Roll-Form Liner FLX068961

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|----------------------|---------------|-------|
| Acrylic | 76 | 836 |
| Glass | 78 | 858 |
| Stainless Steel | 78 | 858 |
| Polypropylene | 72 | 792 |
| Acrylic Powder Paint | 78 | 858 |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|--|-------------|
| Expected Shear (hours) | | |
| Tack (g) | 700 | ASTM D 2979 |
| Expected Exterior Life | Two years | |
| Additional Information | | |
| Service Temperature | -40°F to 176°F (-40°C to 80°C) | |
| Minimum Application Temperature | 32°F (0°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% RH | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.