



Flexcon® PharmCal® TamperMark™ 069051 (PharmCal® PE 200 White Destruct TC-716 V-88 Spec 50K/Q-8)

2.0 Mil White Destructive Polyethylene, Permanent Adhesive, Paper Liner
FLX069051

Benefits

- Destructible film prevents relabeling onto counterfeit package
- Ideal for FDA 21CFR 211.132 and EU Falsified Medicines Directive(FMD) regulations for tamper-proof labeling and packaging
- 6-month change notification

Features

- 2.0 mil destructible white polyethylene destructs or distorts easily
- Topcoat optimizes ink receptivity with flexographic, offset and letterpress inks
- Aggressive permanent rubber based adhesive offers excellent adhesion to plastic containers, cardboard, and packaging materials
- Backed with a 50 lb. semi-bleached kraft release liner that is Quilon®* coated
- UL recognized under UL 969 - UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component

Additional Details

Recommendations: Printing/converting trials are highly recommended prior to full scale manufacturing.

*Quilon® is a registered trademark of Zaclon LLC

"Fit-for-use" testing is recommended under actual application conditions.

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	6.55	
Film	2.0 +/-10%	51
Adhesive	1.0-1.1 +/- 0.1 (3)	25-28
Liner	3.1 +/- 10%	79

Test Method: ASTM D 3652 (Modified for use with non-tape products)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	Film rips	Film rips
Glass	Film rips	Film rips
Polypropylene	Film rips	Film rips
Stainless Steel	Film rips	Film rips

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	630	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.