

Benefits

- UL recognized under UL 969 - UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component

Features

- 2.3 mil hard white polypropylene provides consistent surface smoothness and excellent dimensional stability
- Print-receptive surface is printable via flexographic, UV offset, gravure, UV screen, UV letterpress, thermal transfer, narrow-format UV inkjet, and hot stamping
- High-performance acrylic adhesive adheres well to a variety of surfaces
- Backed with an ultra smooth polyester release liner for excellent adhesive wet out
- Release liner provides a good diecutting base

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	4.45	
Film	2.3 +/- 10 %	58
Adhesive	0.5-0.6 +/- 0.1	13-15 +/- 3
Liner	1.2 +/- 10 %	30

Test Method: ASTM D 3652 (Modified for use with non-tape product)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	54	594
Glass	40	440
Polypropylene	20	220
Acrylic	52	572

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	10	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	730	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	35°F (1.7°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.