

# Flexcon® FlexMark® PP 200 H Clear TC-458 L-01 120 Poly H-9

Consumer Durables Clear Polypropylene - Roll Form FLX069254

#### **Benefits**

• UL recognized under UL 969 - UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component

### **Features**

- 2.0 mil hard clear polypropylene provides consistent surface smoothness and excellent dimensional stability
- High-performance acrylic adhesive adheres well to a variety of surfaces
- Print-receptive surface is printable via flexographic, UV offset, gravure, UV screen, UV letterpress, thermal transfer, narrow-format UV inkjet, and hot stamping
- Backed with an ultra smooth polyester release liner for excellent adhesive wet out
- Release liner provides a good diecutting base

### **Additional Details**

#### **Technical Data**

#### **Physical Properties**

Thickness (Mils [microns])	Mils	Microns
Total Product	4	
Film	2.0 +/- 10 %	51
Adhesive	0.5-0.6 +/- 0.1	13-15 +/- 3
Liner	1.2 +/- 10 %	30

Test Method: ASTM D 3652 (Modified for use with non-tape products)



# Flexcon® FlexMark® PP 200 H Clear TC-458 L-01 120 Poly H-9

Consumer Durables Clear Polypropylene - Roll Form FLX069254

#### **Adhesion Properties**

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	54	594
Acrylic	54	594
Glass	40	440
Polypropylene	23	253

Test Method: ASTM D 903 (Modified for 72 hr. RT dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	5	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	790	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	35°F (1.7°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	re

## **Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.