



Benefits

- Product is thermally diecuttable

Features

- 2.6 mil clear vinyl film offers good surface quality
- Printable via solvent and UV screen, and solvent and UV inkjet
- Permanent aggressive pressure-sensitive acrylic adhesive is filled with metallic flakes for glitter appearance
- 90 lb. moisture stable polycoated layflat release liner ideal for sheet and roll-to-sheet converting
- Excellent layflat release liner properties for printing and converting

Additional Details

Adhesive thickness variation is caused by glitter in the adhesive

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	14.9	
Film	2.6 +/- 10%	66
Adhesive	3.0-6.0 +/- 0.1	76-152 +/- 3
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic	28	308
Glass	30	330
Stainless Steel	31	341
Polypropylene	7	77
Aluminum	31	341

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	1	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	170	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.