



# Flexcon® DPM Aply® 4WPPSAE (PP 400 F White TC-716 L-344 90 PFW Air Egress - UL Rec)

Consumer Durables: Exterior Durable Gloss Topcoated White Polypropylene Air Egress Sheet Form Line  
FLX069796

## Benefits

- Five year outdoor durability based on 2500 hrs. Xenon Arc
- CUL Recognized, L- Adhesives, UL Recognized

## Features

- Gloss topcoated 4.0 mil white polypropylene (vinyl alternative) provides consistent surface smoothness and excellent dimensional stability
- Printable via resin & wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; laser (toner); and narrow-format UV inkjet
- Permanent acrylic pressure-sensitive adhesive bonds well to low- and high-surface energy plastics, painted metal, powder-coated paint, polycarbonate and fiberglass
- High shear and high peel adhesive resists cold flow and oozing
- 90 lb. embossed liner creates air egress channels in the adhesive to eliminate bubbles and wrinkles during application process and post application process
- Liner is ideal for roll-to-sheet and sheet-form converting on most narrow-format presses

## Additional Details

All narrow-format UV inkjet systems are different; therefore, we recommend "fit-for-use" testing. For laser diecutability, please check with your equipment manufacturer. Please note: DPM Aply® with air egress liner is available for sale in North America only. Due to the custom nature of this product, the data presented are based on three or less production runs.

## Technical Data

### Physical Properties

| Thickness (Mils [microns]) | Mils            | Microns     |
|----------------------------|-----------------|-------------|
| Total Product              | 12.25           |             |
| Film                       | 4.0 +/- 10%     | 102         |
| Adhesive                   | 0.9-1.0 +/- 0.1 | 23-25 +/- 3 |
| Liner                      | 6.8 +/- 10%     | 172         |

Test Method: ASTM D 3652 (Modified for use with non-tape product)

**Adhesion Properties**

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel    | 59            | 649   |
| Glass              | 63            | 693   |
| Polypropylene      | 34            | 374   |
| Acrylic            | 67            | 737   |
| Polyethylene       | 17            | 187   |

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

| Additional Properties           | Value   | Test Method |
|---------------------------------|---|-------------|
| Expected Shear (hours)          |   |             |
| Tack (g)                        | 600   | ASTM D 2979 |
| Expected Exterior Life          | Five years based on 2000 hours Xenon arc testing          |             |
| Additional Information          |   |             |
| Service Temperature             | -40°F to 212°F (-40°C to 100°C)                           |             |
| Minimum Application Temperature | 50°F (10°C)   |             |
| Storage Stability               | Two years stored at 70°F (21°C) and 50% relative humidity |             |

**Product Performance and Suitability**

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.