



Flexcon® CompuCal II® TamperMark™ MM 200 Silver Checkerboard MTC-329 L-156 Spec 50K-8

Security / Authenticity Labeling Silver Polyester - Checkerboard Pattern
FLX007007

Benefits

- UL recognized under UL 969 - UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component and UL File No. PGJI2.MH16635 Printing Materials - Component
- View UL PGUU2 for Flexcon® CompuCal II® TamperMark™ Silver Checkerboard Yellow Card
- View UL PGJI2 for Flexcon® CompuCal II® TamperMark™ Silver Checkerboard Yellow Card

Features

- Matte topcoated 2.0 mil silver tamper-evident polyester provides consistent surface smoothness, excellent dimensional stability, and endurance to varying temperatures
- Leaves behind "Checkerboard" pattern
- Printable via UV and solvent screen, UV and water flexo, UV and oil offset, UV letterpress, wax/resin & wax thermal transfer, dry toner, and laser
- High-performance, aggressive permanent acrylic adhesive provides a permanent bond to a wide range of surfaces, including powder coated paint and metal
- Backed with a 50 lb. bleached kraft release liner ideal for roll-form converting
- Liner is suitable for optical sensing on most thermal transfer printers

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	7.1	
Film	2.5 +/- 10 %	64
Adhesive	1.0-1.1 +/- 0.1 (3)	25 - 28
Liner	3.1 +/- 10 %	79

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel		Shows tampering upon removable
Acrylic		
Glass		

Test Method:

Additional Properties	Value	Test Method
Expected Shear (hours)	5	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	880	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 302°F (-40°C to 150°C) Tamper-evident maximum 104°F (40°C)	
Minimum Application Temperature	32°F (0°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.