



Benefits

- Polypropylene is more economical and conformable than polyester and provides a good diecutting base
- Adhesive complies with FDA 175.105 for indirect food contact
- Order custom widths without purchasing a whole master through [Flexcon® FlexChoice™ for Packaging](#)

Features

- Topcoated 2.0 mil hard clear polypropylene (BOPP) offers excellent resistance to shrinkage, moisture, humidity, and product contents
- Film clarity is ideal for achieving the no-label-look
- Excellent surface smoothness allows for optimum ink laydown
- General-purpose removable adhesive provides minimal adhesion bond over time ensuring clean removability
- Adheres to a wide range of container types
- Printable via UV, solvent & water, flexo, UV inkjet (Xeikon Jetrion 4000 series and Domino), UV screen, UV letterpress, and hot stamping
- 40 lb. bleached white kraft release liner ideal for roll-form converting

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	5.2	
Film	2.0 +/- 10 %	51
Adhesive	0.5-0.6 +/- 0.1	13-15 +/- 3
Liner	2.5 +/- 10 %	64

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	17	187
Glass	14	154
Polypropylene	14	154
Polyethylene	6	66
Aluminum	23	253

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	100	ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load)
Tack (g)	290	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-20°F to 212°F (-29°C to 100°C)	
Minimum Application Temperature	40°F (4°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% relative humidity	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.