



## Flexcon® ThermoFilm® HT™ PI2W50GV2

2.0 mil high temperature white polyimide film

FLX070414 | Part #: PI2-DW23-J48AH/36

### Benefits

- UL 969 recognized, REACH & RoHS compliant, and halogen-free
- Chemical, solvent, and abrasion resistance (OHR1 Compliant) for harsh industrial conditions

### Features

- 2 mil (50 micron) high temperature white polyimide film, topcoated for extensive printability
- Withstands intermittent heat up to 750°F (399°C) for high-heat applications
- 600 DPI resolution for sharp barcodes, data matrix codes, and alphanumeric tracking
- ANSI scannability compliance ensures reliable long-term traceability
- Topcoat has static dissipating properties
- Low-outgassing adhesive for sensitive applications

### Additional Details

[Click here](#) for additional information including technical information.

### Technical Data

#### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	7.1	
Film	2.0 +/- 15%	50 +/- 15%
Adhesive	1.4 - 1.5 +/- 0.1	36 - 38 +/- 3
Liner	2.7 +/- 10%	69 +/- 10%
Topcoat 2	19 +/- 15%	

Test Method: ASTM D 3652



# Flexcon® ThermlFilm® HT™ PI2W50GV2

2.0 mil high temperature white polyimide film

FLX070414 | Part #: PI2-DW23-J48AH/36

## Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	51	561
Acrylic	60	660
Glass	49	539
FR4 Board	51	561

Test Method: ASTM D 903

Additional Properties	Value	Test Method
Expected Shear (hours)	1	ASTM D 3654 Method A
Tack (g)	1390	ASTM D 2979
Expected Exterior Life	Two years	
Additional Information		
Service Temperature	-40°F to 356°F (-40°C to 180°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (21°C) and 50% RH	

## Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.