

Benefits

- Topcoat allows for smudge proof and abrasion resistant thermal transfer printing
- Engineered product can withstand temperatures as low as -320.8 °F (-196 °C), making it suitable for use in liquid nitrogen at its boiling point
- Adhesive is engineered to survive extreme temperature cycling including exposure to liquid nitrogen
- Helps to support sustainability efforts and provides the same performance level as a standard polyester liner
- Overall thinner product construction yields more labels per same diameter roll yielding less changeover

Features

- Topcoated 1.0 mil clear matte polypropylene
- Printable via resin & wax/resin thermal transfer; UV & solvent screen; UV, solvent & water flexo; laser (toner); and narrow-format UV inkjet
- Permanent high-tack cold temperature adhesive design for application to glass and plastic tubes and vials
- 1.2 mil polyester release liner manufactured from up to 30% PCW content
- Release liner provides a good diecutting base and allows for high-speed dispensing

Additional Details

- Product complies with 21 CFR 175.105, REACH, and RoHS/WEE
- No raw component substitutions without six-month advance change notification
- Compatible sterilization methods
- Gamma Sterilization (maximum dose~20kGy)
- ETO Sterilization (maximum concentration~400 mg/L)
- Dry heat (recommended 70 °F for label itself)
- Autoclave (recommended only after applying the labels to vials)

Note: For optimum performance in cryogenic environments, die cut the labels so that the longer dimension is parallel with the machine direction (MD) of the material.

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|------------------|--------------|
| Total Product | 3.25 | |
| Film | 1, +/- 10% | 25, +/- 10% |
| Adhesive | 0.6-0.7, +/- 0.1 | 15-18, +/- 3 |
| Liner | 1.2, +/- 10% | 30, +/- 10% |

Test Method:

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel | 65 | 715 |
| Acrylic | 97 | 1067 |
| Glass | 45 | 495 |
| Polypropylene | 21 | 231 |
| Polyethylene | 16 | 176 |

Test Method: ASTM D 903 Modified

| Additional Properties | Value | Test Method |
|---------------------------------|---|----------------------|
| Expected Shear (hours) | <0.5 | ASTM D 3654 Method A |
| Tack (g) | 690 | ASTM D 2979 |
| Expected Exterior Life | Indoor use only | |
| Additional Information | | |
| Service Temperature | -320.8°F to 275°F (-196°C to 135°C) on plastic tubes, PP vials, EVA bags, and paper boxes | |
| Minimum Application Temperature | -320.8°F (-196°C) | |
| Storage Stability | Two years when stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.