

Classics Plus® 10106 Ink Receptive 1 Mil Clear Polyetser Permanent Acrylic Adhesive Sheet Liner

Durable Goods and Equipment Label Clear Polyester FLX007119

Benefits

• UL recognized under UL 969 - UL File No. PGGU2.MH10170 Marking and Labeling System Materials - Component

Features

- 1.0 mil clear polyester (non-vinyl) with good chemical resistance to mild cleaning products
- Printable via solvent screen, solvent flexo, and oil offset
- Permanent acrylic pressure-sensitive adhesive bonds well to a variety of surfaces
- Backed with a layflat 90 lb. moisture stable polycoated release liner ideal for sheet-form converting
- Excellent stayflat release liner properties for printing and converting

Additional Details

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|-----------------|-------------|
| Total Product | 8.87 | |
| Film | 1.0 +/- 10 % | 25 |
| Adhesive | 1.0-1.1 +/- 0.1 | 25-28 +/- 3 |
| Liner | 6.9 +/- 10 % | 175 |

Test Method: ASTM D 3652 (Modified for use with non-tape product)



Classics Plus® 10106 Ink Receptive 1 Mil Clear Polyetser Permanent Acrylic Adhesive Sheet Liner

Durable Goods and Equipment Label Clear Polyester FLX007119

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|--------------------|---------------|-------|
| Stainless Steel | 44 | 484 |
| Glass | 43 | 473 |
| Polypropylene | 14 | 154 |
| Acrylic | 48 | 528 |

Test Method: ASTM D 903 (Modified for 72 hr dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|---|---|
| Expected Shear (hours) | 40 | ASTM D 3654 Method A (1 hr dwell, 1 sq. in, 4 lb. load) |
| Tack (g) | 930 | ASTM D 2979 |
| Expected Exterior Life | Two years | |
| Additional Information | | |
| Service Temperature | -40°F to 302°F (-40°C to 150°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years stored at 70°F (21°C) and 50% relative humidity | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.