



## Benefits

- Flexcon® TracRite™ 120 polyester release liner provides excellent on-press performance for tight-registration graphics, a good diecutting base and allows for high-speed dispensing

## Features

- 2.45 mil flexible white polypropylene offers good diecutting properties and excellent resistance to a variety of environments
- Print-receptive film provides uniform and consistent printability via rotary letterpress, rotary screen and flexography\*
- Aggressive permanent acrylic adhesive, adheres to a wide range of container types including low-surface HDPE

## Additional Details

### Technical Data

#### Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	4.55	
Film	2.35 +/- 10 %	60
Adhesive	0.5-0.6 +/- 0.1	17-19 +/- 3
Liner	1.2 +/- 10 %	30

Test Method: ASTM D 3652 (Modified for use with non-tape product)



#### Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Stainless Steel	63	693
Acrylic	66	726
Glass	58	638
Polypropylene	7	77

Test Method: ASTM D 903 (Modified for 72 hr. dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)	Erratic	ASTM D 3654 Method A (1 hr. dwell, 1 sq. in, 4 lb. load)
Tack (g)	590	ASTM D 2979
Expected Exterior Life	Indoor use only	
Additional Information		
Service Temperature	-40°F to 212°F (-40°C to 100°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability		

## Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.