

Flexcon® Classics Plus® Select™ 50285SL Ink Receptive Roll Form 1.5 MIL Clear PET with Adhesive

Novelty Stickers - Clear - Permanent - Roll Form FLX000009

Benefits

Roll-form liner is a semi-bleached kraft release liner for ease of converting and manual dispensing

Features

- 1.5 mil super clear polyester film provides excellent clarity and durability
- Ink-receptive surface is compatible with most standard flexographic inks. Please test for ink adhesion with your specific ink chemistry
- Permanent pressure-sensitive acrylic adhesive bonds well to a variety of surfaces including low surface energy plastics, paper, wood, glass and metal
- Removable pressure-sensitive acrylic adhesive bonds well to a variety of surfaces including chrome-coated metal, chrome-coated plastic, glass, auto glass and painted plastic
- 50 lb. bleached kraft release liner offers good diecutability

Additional Details

Technical Data

Physical Properties

| Thickness (Mils [microns]) | Mils | Microns |
|----------------------------|---------------------|---------|
| Total Product | 5.76 | |
| Film | 1.4 +/- 10% | 36 |
| Adhesive | 0.8-0.9 +/- 0.1 (3) | 20-23 |
| Liner | 3.1 +/- 10% | 79 |

Test Method: ASTM D 3652 (Modified for use with non-tape products)



Flexcon® Classics Plus® Select™ 50285SL Ink Receptive Roll Form 1.5 MIL Clear PET with Adhesive

Novelty Stickers - Clear - Permanent - Roll Form FLX000009

Adhesion Properties

| Ultimate Peel from | Average Oz/In | (N/m) |
|-----------------------|---------------|-------|
| Auto Glass | 35 | 385 |
| Chrome-Coated Meta | 29 | 319 |
| Chrome-Coated Plastic | 34 | 374 |
| Glass | 30 | 330 |
| Painted Plastic | 38 | 418 |

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

| Additional Properties | Value | Test Method |
|---------------------------------|--|-------------|
| Expected Shear (hours) | | |
| Tack (g) | 340 | ASTM D 2979 |
| Expected Exterior Life | Two years | |
| Additional Information | Chemical Resistance Water Excellent ASTM D 896 (Modified for number of cycles and cycle time) Gasoline Poor Basic Cleaners Excellent Toluene Poor | 5 |
| Service Temperature | -40°F to 302°F (-40°C to 150°C) | |
| Minimum Application Temperature | 50°F (10°C) | |
| Storage Stability | Two years when stored at 70°F (21°C) and 50% relative humidity $$ | |

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.