

Benefits

- ASTM D4956 - Reflective Sheeting
- 7 year outdoor durability

Features

- 2 mil acrylic film with 2 mil reflective glass bead coating
- Compatible with a wide range of conventional print methods (we recommend evaluating the intended ink system for compatibility with the product under the application conditions)
- Excellent chemical and scratch resistance
- High-performance permanent acrylic adhesive bonds well to ABS, aluminum and stainless steel surfaces
- Backed with a 90 lb. moisture stable polycoated layflat release liner ideal for sheet-form converting

Additional Details

Technical Data

Physical Properties

Thickness (Mils [microns])	Mils	Microns
Total Product	12.95	
Film	4.0 +/- 15%	102
Adhesive	1.2-1.3 +/- 0.1 (3)	30-33
Liner	6.9 +/- 10%	175

Test Method: ASTM D 3652 (Modified for use with non-tape products)

Adhesion Properties

Ultimate Peel from	Average Oz/In	(N/m)
Acrylic		Film rips during the adhesion
Glass		Film rips during the adhesion
Stainless Steel		Film rips during the adhesion

Test Method: ASTM D 903 (Modified for 72 hour dwell time)

Additional Properties	Value	Test Method
Expected Shear (hours)		
Tack (g)	850	ASTM D 2979
Expected Exterior Life	Seven years	
Additional Information		
Service Temperature	-40°F to 176°F (-40°C to 80°C)	
Minimum Application Temperature	50°F (10°C)	
Storage Stability	Two years stored at 70°F (10°C) and 50% RH	

Product Performance and Suitability

Descriptive information, performance data, and recommendations for Flexcon products are guides and not specifications. Providing this information is to assist you and does not constitute a warranty of any kind by Flexcon.

Purchasers must independently determine the material's suitability for their intended use. No distributor, salesman, or representative of Flexcon is authorized to provide any warranty or guarantee beyond what is stated. FLEXCON MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, COURSE OF PERFORMANCE, OR TRADE USAGE.